

This document is an excerpt from the Woodward original document No.: 3-OF-02334, Rev. E related to Printed Circuit Boards (PCBs).

6.2.4.1 PWB / PCB Specifications

PWBs shall be handled and stored in accordance with a process that is compliant to the guidance found within IPC-1601. Deviations from any of these recommendations require written approval from Woodward AS prior to their use. All materials used for packaging and shipping of PCBs shall be free of sulfur and chlorine. All PCBs shall be shipped in vacuum sealed containers. Sulfur free paper shall be placed between PCB and packaging film and sulfur free desiccant shall be added to each vacuum sealed container. **If the moisture content of the board cannot be guaranteed via process control, the PWB shall be baked prior to use per IPC-1602.

PWBs should comply with the criteria within IPC-A-600 for Class 3 products.
